


CONTRAFLAM® 60-3

Fire resistant safety glass for interior application

CLASSIFICATION



EI = Insulation

Ability to withstand fire exposure without transmission of fire to the non-fire side as a result of the passage of flames or hot gases or significant conduction of heat, thereby causing ignition of the non-fire exposed surface or materials in contact, and provides a barrier to heat to protect people.

AVAILABLE OPTIONS



- + Alarm
- + EMS shielding
- + Floors
- + Protection



- + Coloring
- + Digital printing
- + Matt finished
- + Screen printing
- + Shapes



- + Climate control
- + Dynamic privacy
- + Extra clear
- + Noise control
- + Screen



- + Double glazing
- + Self-cleaning
- + Solar control
- + Tinting
- + Triple glazing

Contact us to personalize your solution to meet your project requirements.

TECHNICAL SPECIFICATIONS*

Fire resistance

	EI 60 (EN 13501-2)
Reaction to fire	A2-s1, d0 (EN13501-1)
Impact resistance	1(B)1 (EN 12600)
UV Stability	Yes (EN ISO 12543-4), no formation of bubbles or yellowing after 2000 hours of exposure to radiation
Application conditions	Avoid prolonged exposure to elevated temperatures. See Quality Guideline, Application Instructions.
Certificate of constancy of performance	0336-CPR-5064C/IL - AVCP System 1
Hazardous material contained	None
Dimensional tolerances (height/width)	≤1000mm: -1/+2mm ≤2000mm: -1/+2.5mm >2000mm: -1/+3mm

Product

	CONTRAFLAM 60-3		
Nominal thickness	27 mm	31 mm	41 mm
Maximum glass size	Based on Certification; Please get in touch with Vetrotech representative for more information		
Thickness tolerance	+2 / -2 mm	+2 / -2 mm	+2 / -2 mm
Basic glass	Planilux India	Planilux India	Planilux India
Weight	59 kg/m ²	69 kg/m ²	93.5 kg/m ²
Sound reduction Rw (EN 140-3)	43 (-2, -2) dB	43 (-2, -3) dB	44 (-2, -3) dB
Light transmission (EN 410)	81%	81%	78%
Light reflection pL ext./int. (EN 410)	10% / 10%	10% / 10%	9% / 9%
U value (EN 673)	4.3 W/m ² K	4.3 W/m ² K	4.2 W/m ² K
g value (EN 410)	0.65	0.65	0.58
Energy transmission tE (EN410)	56%	56%	49%

*Valid for products manufactured at the 'World Glass Complex' of Saint-Gobain India Pvt. Ltd. - Vetrotech Business
Shapes: dimensional tolerance may vary +1mm